Nabertherm

MORE THAN HEAT 30-3000 °C

Material-ID	100013
Hersteller	Vita Zahnfabrik
Beschreibung	Reserve
Material Name	VITA SUPRINITY PC

	Prozesse	Vortrocknen					Schließen					Vorwärmen					Brennen 1					Brennen 2					Brennen 3					Kühlen				
Programm-nummer	Name	Freigeschaltet	Rate [°/min]	Temperatur [°]	Haltezeit [s]	Vakuum	Freigeschaltet	Rate [°/min]	Temperatur [°]	Haltezeit [s]	Vakuum	Freigeschaltet	Rate [°/min]	Temperatur [°]	Haltezeit [s]	Vakuum	Freigeschaltet	Rate [°/min]	Temperatur [°]	Haltezeit [s]	Vakuum	Freigeschaltet	Rate [°/min]	Temperatur [°]	Haltezeit [s]	Vakuum	Freigeschaltet	Rate [°/min]	Temperatur [°]	Haltezeit [s]	Vakuum	Freigeschaltet	Rate [°/min]	Temperatur [°]	Haltezeit [s]	Vakuum
1	Kristallisation						x		400	240							x	55	830	480	x											x		600	1	
2																																				

Material-ID	100013
Manufacturer	Vita Zahnfabrik
Description	Reserve
Material name	VITA SUPRINITY PC

	Processes	Predrying					Closing					Preheating					Firing 1					Firing 2					Firing 3					cooling				
Program number	Name	Enable	Rate [°/min]	Temperature [°]	Hold time [s]	Vacuum	Enable	Rate [°/min]	Temperature [°]	Hold time [s]	Vacuum	Enable	Rate [°/min]	Temperature [°]	Hold time [s]	Vacuum	Enable	Rate [°/min]	Temperature [°]	Hold time [s]	Vacuum	Enable	Rate [°/min]	Temperature [°]	Hold time [s]	Vacuum	Enable	Rate [°/min]	Temperature [°]	Hold time [s]	Vacuum	Enable	Rate [°/min]	Temperature [°]	Hold time [s]	Vacuum
1							x		400	240							x	55	830	480	x											x		600	1	
2																																				