Material-ID	100068
Hersteller	Vita Zahnfabrik
Beschreibung	Reserve
Material Name	In-Ceram 2000 YZ

	Prozesse	Vortrocknen					Schließen					Vorwärmen					Brennen 1					Brennen 2					Brennen 3					Kühlen				
Programm-nummer	Name	Freigeschaltet	Rate [°/min]	Temperatur [°]	Haltezeit [s]	Vakuum	Freigeschaltet	Rate [°/min]	Temperatur [°]	Haltezeit [s]	Vakuum	Freigeschaltet	Rate [°/min]	Temperatur [°]	Haltezeit [s]	Vakuum	Freigeschaltet	Rate [°/min]	Temperatur [°]	Haltezeit [s]	Vakuum	Freigeschaltet	Rate [°/min]	Temperatur [°]	Haltezeit [s]	Vakuum	Freigeschaltet	Rate [°/min]	Temperatur [°]	Haltezeit [s]	Vakuum	Freigeschaltet	Rate [°/min]	Temperatur [°]	Haltezeit [s]	Vakuum
1	Reinigungsbrand	x		600	180		x		600	180							x	33	700	300																
2	Regenerationsbrand	x		500			x		500	300							x	100	1000	900																

Material-ID	100068
Manufacturer	Vita Zahnfabrik
Description	Reserve
Material name	In-Ceram 2000 YZ

	Processes	Predrying					Closing					Preheating					Firing 1					Firing 2					Firing 3					Cooling				
Program number	Name	Enable	Rate [°/min]	Temperature [°]	Hold time [s]	Vacuum	Enable	Rate [°/min]	Temperature [°]	Hold time [s]	Vacuum	Enable	Rate [°/min]	Temperature [°]	Hold time [s]	Vacuum	Enable	Rate [°/min]	Temperature [°]	Hold time [s]	Vacuum	Enable	Rate [°/min]	Temperature [°]	Hold time [s]	Vacuum	Enable	Rate [°/min]	Temperature [°]	Hold time [s]	Vacuum	Enable	Rate [°/min]	Temperature [°]	Hold time [s]	Vacuum
1	Cleansing firing	x		600	180		x		600	180							x	33	700	300																
2	Regeneration firing	x		500			x		500	300							x	100	1000	900																